

Technical Data Sheet - KahlJelly 7038 Coco

Characteristics

KahlJelly 7038 Coco is a special blend of natural waxes and oils in vegan quality. It offers multifunctional activity and can be used in all kinds of color cosmetics, skin, and hair care applications. KahlJelly 7038 Coco has a soft skin feel, improves viscosity and gloss, and has film-forming properties.

Recommended for

- | | |
|--|---|
| <input checked="" type="checkbox"/> Industrial Application | <input checked="" type="checkbox"/> Personal Care |
| <input type="checkbox"/> Pharma | <input type="checkbox"/> Food |

Compliance status

- | | |
|---|---|
| <input checked="" type="checkbox"/> Natural Cosmetics | <input type="checkbox"/> European Pharmacopoeia |
| <input type="checkbox"/> Organic Cosmetics | <input type="checkbox"/> USP/NF |

General

Parameter		Unit
INCI (EU)	Cocos Nucifera Oil, Olea Europaea Fruit Oil, Rhus Verniciflua Peel Cera, Helianthus Annuus Seed Cera	
CAS no.	8001-31-8, 8001-25-0, 225234-38-8, 1286686-34-7	
Color	off-white	
Appearance	hot fill	
Shelf life	365	days
Penetration	approx. 120 dmm	

Color and shape of the product may differ slightly within a production batch due to the production process.

This product information is indicative and does not include any guarantee. It does not relieve the purchaser from examining the product upon delivery and gives no assurance of stability of the product for any particular purpose.

Technical Data Sheet - KahlJelly 7038 Coco

Specification

Parameter		Unit
Drop point	58 - 64	°C
Saponification value	230 - 250	mg KOH/ g
Peroxide value	max. 5	meq/ kg

Please note that due to the chemical composition, the texture of this product may change after melting and cooling. This does not imply any loss of quality. Please melt and stir before using.

Automatically generated and valid without signature
01.09.2023 / 0000279539

Last amended on: 01.09.2023

This product information is indicative and does not include any guarantee. It does not relieve the purchaser from examining the product upon delivery and gives no assurance of stability of the product for any particular purpose.